

colorlac

COLOR YOUR BUSINESS



SOLUTIONS WOOD





Unlimited miscibility with each other // Good light fastness // High concentration

DESCRIPTION / PKL are solvent-based concentrated pastes in long-oil alkyd resin.

UTILIZATION / suitable for impregnating stains, oils, synthetic waxes, base and top coats.

MISCIBILITY / The products of PKL series are miscible with each other in any ratio to allow you to independently create new customized solutions.

SPRAY APPLICATION / Dilute the paste 1:10 in solvent-based top coats.

To know the compatibility with your system, you should check with prior examination by consulting our laboratory technicians.

CODE	COLOR INDEX	DRY MATTER	DENSITY	PIGMENT CONC.	SOLUBILITY			
					WATER	PM	ACETONE	LIGHT FASTNESS
PKL 1302	PIGMENT WHITE 6	87 ± 3%	1,95 Kg/l ± 2%	70 ± 3%	-			8
PKL 3201	PIGMENT YELLOW 42	72 ± 3%	1,39 Kg/l ± 2%	45 ± 3%		-		8
PKL 3301	PIGMENT YELLOW 42	81 ± 3%	1,60 Kg/l ± 2%	55 ± 3%		-		8
PKL 3303	PIGMENT YELLOW 184	86 ± 3%	1,85 Kg/l ± 2%	60 ± 3%		_		8
PKL 4102	PIGMENT BLUE 15:4	58 ± 3%	1,00 Kg/l ± 2%	25 ± 3%		_		7/8
PKL 6307	PIGMENT BLACK 7	62 ± 3%	1,01 Kg/l ± 2%	25 ± 3%		-		8
PKL 8106	PIGMENT RED 170	60 ± 3%	0,97 Kg/l ± 2%	28 ± 3%			-	7/8
PKL 8201	PIGMENT RED 101	72 ± 3%	1,42 Kg/l ± 2%	45 ± 3%			-	8
PKL 8301	PIGMENT RED 101	86 ± 3%	1,75 Kg/l ± 2%	60 ± 3%			-	8
PKL 9101	PIGMENT GREEN 7	56 ± 3%	1,00 Kg/l ± 2%	25 ± 3%				8

Table legend: -- no - poor -/+ fair + good

CONCENTRATED LONG OIL PASTES

PKL 8201 / C.I. PIGMENT RED 101

PKL 6307 / C.I. PIGMENT BLACK 7

PKL 1302 / C.I. PIGMENT WHITE 6	PKL 3303 / C.I. PIGMENT YELLOW 184	PKL 3301 / C.I. PIGMENT YELLOW 42			
PKL 3201 / C.I. PIGMENT YELLOW 42	PKL 8106 / C.I. PIGMENT RED 170	PKL 8301 / C.I. PIGMENT RED 101			
TDACDADENT					





PKL 4102 / C.I. PIGMENT BLUE 15:4



Wood

\rightarrow.

•

Solvent

Semi-trasparent

Pigment

^{*} Colors are only for illustrative purpose and may differ slightly from real tones